



WILLIAM FARHAT CORPORATION

ZALKA- AMARET CHALHOUB  
P.O.BOX 90008  
BEIRUT-LEBANON  
TEL/FAX + (961) 1 885880  
TEL/FAX + (961) 1 886666  
MOBILE + (961) 3 679922  
EMAIL: info@wifar.com  
WWW.WILFAR.COM

## TARANTO

TYPE OF LEATHER	BOVINE
ORIGIN	EUROPEAN AND NON-EUROPEAN
THICKNESS	MM. 0.9 1.00+/- 0.1
AVERAGE SIZE	4 - 4.5 M2
TANNAGE	CHROME SALTS
DYE	ANYLINE DYE
FINISHING	SEMI-ANILINE
APPEARANCE	SEMI-GLOSS

ANALYSIS	TEST METHOD	UNIT MEASUREMENT	RECOMMENDED VALUE
COLOR FASTNESS TO DRY RUBBING 500 CYCLES	UNI EN ISO 11640	GREY scale	4
	UNI EN ISO 11641		
COLOR FASTNESS TO WET RUBBING 80 CYCLES	UNI EN ISO 11640	GREY scale	3/4
	UNI EN ISO 11641		
COLOR FASTNESS TO ALKALINE SWEAT 50 CYCLES	UNI EN ISO 11640	GREY scale	3/4
	UNI EN ISO 11641		
FINISH ADHESION	UNI EN ISO 11644	N/10MM	2
PH	UNI EN ISO 4045	-	3.5
TEAR STRENGTH	UNI EN ISO 3377-1	N	20
COLOR FASTNESS TO LIGHT XENOTEST	UNI EN ISO 105 B02	BLUE SCALE	4
COLOR FASTNESS TO LIGHT XENOTEST-WHITE COLOUR	UNI EN ISO 105 B02	BLUE SCALE	3
FLAMMABILITY	UNI EN 1021-1:2006	-	NO IGNITION
FLAMMABILITY	UNI EN 1021-2:2006	-	NO IGNITION
CIGARETTE TEST (CALIFORNIA)	TB117		PASS

### DISCLAIMER

All submitted tests results are obtained using official methods on non-manipulated leather.