

CLARA

TECHNICAL DATA

WEIGHT	970 g/lm
WIDTH	140 cm
PILLING ASTM D3512	4
ABRASION/MARTINDALE	> 50 000
COLOR FASTNESS TO LIGHT	> 5
COLOR FASTNESS TO RUBBING	4-5 DRY 4 WET
SEAM SLIPPAGE RESISTANCE EN ISO 13936-2	WARP 4.0 MM
	WEFT 4.0 MM
TENSILE STRENGTH EN ISO 13934-1	WARP 2100 N
	WEFT 1400 N
TEAR GROWTH RESISTANCE EN ISO 13937-3	WARP 580 N
	WEFT 470 N
SURFACE / BACKING COMPOSITION	5% LINEN + 21% COTTON + 74% POLYESTER
FLAME RETARDANT	BS 5852 PART 1 - CIGARETTE TEST PASS
	EN 1021 - CIGARETTE TEST PASS
	CA TECH BULL 117:2013 / NFPA 260 - CIGARETTE TEST PASS