



DRAYTON



Technical Specifications

Weight	253 g/m2
Width	140 cm
Pilling ASTM D3512	3.5
Abrasion/martindale	93 000 DoubleRubs
Cleaning Code	W
Direction	RR
Repeat	N/A
Seam Slippage	96.6 lbs Warp
ASTM D 4034	100.9 lbs Filling
Tensile Strength	106.1 lbs Warp
ASTM D 5034	142.7 lbs Filling
Backing	Coating
Composition	100% Polyester

Applications & Features



Flammability Norms
CALIFORNIA TB 117-2013

Clean and Care

- Frequent wash may affect the performance of the product.
- Any stain, spills or soiling should be cleaned up promptly with a neutral soap solution using a cloth in smooth circular movements.
- We do not accept responsibility for any damage resulting from inappropriate use, chemical cleaning or additional impregnation.

The analytical results are referred only to the sample tested. Discoloration and colour deviations tolerated by permissible industrial standards do not constitute reasons for claims. Colour migration may occur. Pilling is a natural phenomenon that occurs due to daily use and frequent washing and cannot be avoided. We reserve the right to modify, at any moment and without notice, any product specifications.



WASH



BLEACH



DRY



IRON



DRYCLEAN



LEBANON
WILLIAM FARHAT CORPORATION
Farhat Bldg, Ground floor,
Blvd. Pr Michel El Murr,
Zalka, Amaret Chalhoub, Beirut
+961 3 679 922 sales@wilfar.com

SAUDI ARABIA
شركة وليم فرحات للديكور
CR# 1009143680
Tamouh Bldg 3rd floor Office 23, Prince Saoud Bin
Abdullah Bin Alwi Street, Al-Quirawan, Riyadh
+966 54 513 3783 sales@wilfar.com

UNITED ARAB EMIRATES
WILFAR L.L.C - FZ
CR# 104551047400001
Meydan Grandstand, 6th floor, Meydan Road,
Nad Al Sheba, Dubai
+971 56 743 5644 sales@wilfar.com