



WILLIAM FARHAT CORPORATION

ZALKA- AMARET CHALHOUB
P.O.BOX 90008
BEIRUT-LEBANON
TEL/FAX + (961) 1 885880
TEL/FAX + (961) 1 886666
MOBILE + (961) 3 679922
EMAIL: info@wilfar.com
WWW.WILFAR.COM

DUMAINE

TECHNICAL DATA

WEIGHT	520 g/m ²
WIDTH	140 cm
PILLING ASTM D3512	3.5
ABRASION/MARTINDALE	75 000 Double Rubs
DIRECTION	RR
RAILROADED	N/A
SEAM SLIPPAGE	77.6 lbs Warp
ASTM D 4034	40.4 lbs Filling
TENSILE STRENGTH	117.5 lbs Warp
ASTM D 5034	113.3 lbs Filling
BACKING	SPRAY BACKING
COMPOSITION	100% POLYESTER
FLAME RETARDANT	CALIFORNIA TB 117-2013