




NABUCCO Natural Leather



Technical Specifications

Description	Naturally Finished Leather · Writing Effect
Origin	European Bulls · Italy
Average Hide Area	5.50–6.00 sqm
Thickness	1.2–1.3 mm
Light Fastness ISO 105-B02	Blue Scale ≥ 3
Flexing Test ISO 5402	50.000 cycles · No Cracks
Finish Adhesion ISO 11644	N/A
Colour Fastness to Rubbing — Dry ISO 11640 · 50 cycles	≥ 3
Colour Fastness to Rubbing — Wet ISO 11641 · 10 cycles	≥ 3
Tensile Strength ISO 3376	$\geq 10 \text{ N/mm}^2$
Tear Strength ISO 3377-2	$\geq 60 \text{ N}$

Applications & Features



Fire Retardant

UNI EN 1021-1 (BS 5852 Part 1) – Complies



REACH Compliant · Respects the Environment

Respects the environment through application of new technologies in the production process

Clean and Care

- Dust regularly with a soft, dry cloth to keep the surface clean.
- Clean occasionally with a slightly damp cloth using a neutral, non-detergent soap; wipe dry immediately.
- Avoid solvents, detergents, bleach and abrasive cleaners. Keep away from direct heat sources and prolonged sunlight.
- Treat premium leathers periodically with a suitable leather conditioner.

All submitted test results are obtained using official methods on non-manipulated leather. Natural markings, healed scars, wrinkles and grain or shade variations are inherent characteristics of genuine leather and are not considered defects. We reserve the right to modify, at any moment and without notice, any product specifications.



WIPE



NO BLEACH



DRY



NO IRON



NO SOAK



LEBANON
WILLIAM FARHAT CORPORATION
Farhat Bldg, Ground floor,
Blvd. Pr Michel El Murr,
Zalka, Amaret Chalhoub, Beirut
+961 3 679 922 sales@wilfar.com

SAUDI ARABIA
شركة وليم فرحات للديكور
CR# 1009143680
Tamouh Bldg 3rd floor Office 23, Prince Saoud Bin
Abdullah Bin Alwi Street, Al-Quirawan, Riyadh
+966 54 513 3783 sales@wilfar.com

UNITED ARAB EMIRATES
WILFAR L.L.C - FZ
CR# 104551047400001
Meydan Grandstand, 6th floor, Meydan Road,
Nad Al Sheba, Dubai
+971 56 743 5644 sales@wilfar.com