



WILLIAM FARHAT CORPORATION

ZALKA- AMARET CHALHOUB
P.O.BOX 90008
BEIRUT-LEBANON
TEL/FAX + (961) 1 885880
TEL/FAX + (961) 1 886666
MOBILE + (961) 3 679922
EMAIL: info@wilfar.com
WWW.WILFAR.COM

NABUCCO

TYPE OF LEATHER	BOVINE
ORIGIN	EUROPEAN
THICKNESS	MM. 1.2-1.3
AVERAGE SIZE	4.5 - 5.2 M2
DYE	ANILINE DYE
FINISHING & APPEARANCE	NABUK LEATHER

ANALYSIS	TEST METHOD	UNIT MEASUREMENT	RECOMMENDED VALUE
LIGHT FASTNESS	ISO105/ B02	24H CON XENO ISO5	≥3 BLUE SCALE
FLEX	ISO 5402	20.000 CYCLES	NO CRACKS
ADESION TO FINISH	ISO 11644	≥2.5N/CM	NO CRACKS
COLOR FASTNESS TO RUBBING	ISO 11640	DRY 50 CYCLES	≥3
	ISO 11641	WET 20 CYCLES	≥3
COLOR FASTNESS TO WATER SPOTTING	ISO 15700	GREY SCALE	≥3
COLD CRACK TEMPERATURE OF SURFACE COATING	ISO 17233	-15°	NO CRACKS
FORMALDEHYDE	ISO 17226-1	PPM	≤150
FLAMMABILITY	UNI EN 1021-1	BS 5852 PART 1	COMPLIES

DISCLAIMER

All submitted tests results are obtained using official methods on non-manipulated leather.