



WILLIAM FARHAT CORPORATION

ZALKA- AMARET CHALHOUB
P.O.BOX 90008
BEIRUT-LEBANON
TEL/FAX + (961) 1 885880
TEL/FAX + (961) 1 886666
MOBILE + (961) 3 679922
EMAIL: info@wilfar.com
WWW.WILFAR.COM

ERDO FR

TECHNICAL DATA

TEST TYPES	ASPECT	NORM	UNIT	STANDART
WEIGHT		630±5%	g/m ²	ISO 2286-2
THICKNESS		1,00±5%	mm	ISO 2286-3
TENSILE STRENGHT	ACROSS	min. 400	N	ISO 1421
	ALONG	min. 400	N	ISO 1421
TEAR STRENGHT	ACROSS	min. 25	N	ISO 4674-2
	ALONG	min.35	N	ISO 4674-2
ELONGATION AT BREAK	ACROSS	min.80±20%	%	ISO 1421
	ALONG	min. 100±20%	%	ISO 1421
FLEXING ENDURANCE	at -5°C	min.100000	FLX	ISO 5402
MARTINDALE		min. 100000	RUB	ISO 5470-2
COLOR FASTNESS TO RUBBING	DRY	min. 5	GS	ISO 105X12
	WET	min. 5	GS	ISO 105X12
LIGHT FASTNESS	LIGHT COLORS	min.5	BW	ISO 105B02
	DARK COLORS	min. 5	BW	ISO 105B02
PEEL ADHESION		min. 40	N	ISO 2411

CHEMICAL CHARACTERISTICS

COMPOSITION	UNIT	VALUE
POLYURETHANE	%	3
POLYVINYL CHLORIDE	%	65
ORGANIC/MINERAL COMPOUNDS	%	32
BACKING / POLYESTER	%	100

STANDARDS

FIRE RESISTANCE STANDARDS

- ECE-R-118.02 (Annex 6,7,8) EE
- Cal TB 116 & 117/ CA 133/ NFPA 260 (USA)
- BS 5852 Part I Ignition Source 1 (Cigarette & Match)
- IMO FTP Code Annex 1 Part 8
- EN 1021 Part 1 & 2

Valid for all colors. (Red colors may have less color fastness to rubbing)

