



FREEPORT



Technical Specifications

Weight

ISO 2286-2

600±5% g/m²

Thickness

ISO 2286-3

1,15±5% mm

Surface Composition

2% PU · 80% PVC
· 18% Polyester

Tensile Strength

ISO 1421

Across min. 200 N
Along min. 200 N

Tear Strength

ISO 4674-2

Across min. 20 N
Along min. 30 N

Elongation at Break

ISO 1421

Across
min. 80±20%
Along min.
100±20%

Flexing Endurance

ISO 5402

At -5°C min. 100000
FLX

Martindale

ISO 5470-2

min. 50000 RUB

Colour Fastness to Rubbing

ISO 105X12

Dry min. 4-5 GS
Wet min. 4-5 GS

Light Fastness

ISO 105B02

Light Colors min. 4
BW
Dark Colors min. 5
BW

Peel Adhesion

ISO 2411

min. 30 N

Applications & Features



Flammability Norms

Cal TB 116 & 117/ CA 133/ NFPA 260 (USA) · BS 5852 Part I Ignition Source 1 (Cigarette & Match) · IMO FTP Code Annex 1 Part 8 · EN 1021 Part 1 & 2



IMO FTP Code

Annex 1 Part 8

Clean and Care

- Wipe clean with a soft damp cloth and mild soap solution; wipe dry.
- Avoid solvents, bleach and abrasive cleaners.
- We do not accept responsibility for any damage resulting from inappropriate use or additional treatment.

Valid for all colours. Red colours may have lower colour fastness to rubbing. All submitted test results are obtained using official methods on non-manipulated material. We reserve the right to modify, at any moment and without notice, any product specifications.



WIPE



BLEACH



DRY



IRON



DRYCLEAN



LEBANON
WILLIAM FARHAT CORPORATION
Farhat Bldg, Ground floor,
Blvd. Pr Michel El Murr,
Zalka, Amaret Chalhoub, Beirut
+961 3 679 922 sales@wilfar.com

SAUDI ARABIA
شركة وليم فرحات للديكور
CR# 1009143680
Tamouh Bldg 3rd floor Office 23, Prince Saoud Bin
Abdullah Bin Alwi Street, Al-Quirawan, Riyadh
+966 54 513 3783 sales@wilfar.com

UNITED ARAB EMIRATES
WILFAR L.L.C - FZ
CR# 104551047400001
Meydan Grandstand, 6th floor, Meydan Road,
Nad Al Sheba, Dubai
+971 56 743 5644 sales@wilfar.com