



SPRING FR



Technical Specifications

Weight ISO 2686-2	600±5% g/m²
Thickness ISO 2686-3	1,25±5% mm
Surface Composition	2% PU · 76% PVC · 22% Polyester
Tensile Strength ISO 1421	Across min. 245 N Along min. 500 N
Tear Strength ISO 4674-2	Across min. 35 N Along min. 30 N
Elongation at Break ISO 1421	Across min. 200±20% Along min. 60±20%
Flexing Endurance 7854	At -5°C min. 100000 FLX
Martindale DIN 53863	min. 75000 RUB
Colour Fastness to Rubbing ISO 105X12	Dry min. 5 GS Wet min. 5 GS
Light Fastness ISO 105B02	Light Colors min. 6 BW Dark Colors min. 6 BW
Peel Adhesion ISO 2411	min. 45 N

Applications & Features



Flammability Norms

ECE-R-118 .02 (Annex 6,7,8) · EE · FMVSS 302 /CMVSS 302 · Cal TB 116 & 117/ CA 133/ NFPA 260 (USA) · BS 5852 Part I Ignition Source 1 (Cigarette & Match) · IMO FTP Code Annex 1 Part 8 · EN 1021 Part 1 & 2 ·
WATERPROOF This product has waterproof property which provides comfortable usage in marine - outdoor applications · **HYDROLYSIS** 14+Weeks ASTM D3690-02 Sect. 6.11 (Hydrolytic Stability) ISO 1419 Method C (Accelerated Ageing) · **ANTIMICROBIAL & ANTIFUNGAL** According to the test reports of SANITIZED laboratories in Switzerland, this product contains special additives granting protection against microorganisms · **SALT-CHLORE-UV RESISTANCE** This product contains special additives providing high resistance against salt, chlore and UV light.



IMO FTP Code

Annex 1 Part 8

Clean and Care

- Wipe clean with a soft damp cloth and mild soap solution; wipe dry.
- Avoid solvents, bleach and abrasive cleaners.
- We do not accept responsibility for any damage resulting from inappropriate use or additional treatment.

Valid for all colours. Red colours may have lower colour fastness to rubbing. All submitted test results are obtained using official methods on non-manipulated material. We reserve the right to modify, at any moment and without notice, any product specifications.



WIPE



BLEACH



DRY



IRON



DRYCLEAN



LEBANON
WILLIAM FARHAT CORPORATION
Farhat Bldg, Ground floor,
Blvd. Pr Michel El Murr,
Zalka, Amaret Chalhoub, Beirut
+961 3 679 922 sales@wilfar.com

SAUDI ARABIA
شركة وليم فرحات للديكور
CR# 1009143680
Tamouh Bldg 3rd floor Office 23, Prince Saoud Bin
Abdullah Bin Alwi Street, Al-Quirawan, Riyadh
+966 54 513 3783 sales@wilfar.com

UNITED ARAB EMIRATES
WILFAR L.L.C - FZ
CR# 104551047400001
Meydan Grandstand, 6th floor, Meydan Road,
Nad Al Sheba, Dubai
+971 56 743 5644 sales@wilfar.com