



NATUR Pearlized Leather



Technical Specifications

Description

**Pearlized Effect
Leather**

Origin

**European Bulls ·
Italy**

Average Hide Area

5.50–6.00 sqm

Thickness

1.2–1.3 mm

Light Fastness

ISO 105-B02 · 72h

Blue Scale 6/7

Flexing Test

ISO 5402

**50.000 cycles · No
Cracks**

Finish Adhesion

ISO 11644

≥ 2 N/cm²

Tensile Strength

ISO 3376

≥ 5 N/mm²

Tear Resistance

ISO 3377-2

≥ 40 N

Applications & Features



Fire Retardant

UNI EN 1021-1 (BS 5852 Part 1) – Complies



REACH Compliant · Respects the Environment

Respects the environment through application of new technologies in the production process

Clean and Care

- Dust regularly with a soft, dry cloth to keep the surface clean.
- Clean occasionally with a slightly damp cloth using a neutral, non-detergent soap; wipe dry immediately.
- Avoid solvents, detergents, bleach and abrasive cleaners. Keep away from direct heat sources and prolonged sunlight.
- Treat premium leathers periodically with a suitable leather conditioner.

All submitted test results are obtained using official methods on non-manipulated leather. Natural markings, healed scars, wrinkles and grain or shade variations are inherent characteristics of genuine leather and are not considered defects. We reserve the right to modify, at any moment and without notice, any product specifications.



WIPE



NO BLEACH



DRY



NO IRON



NO SOAK



LEBANON
WILLIAM FARHAT CORPORATION
Farhat Bldg, Ground floor,
Bldv. Pr Michel El Murr,
Zalka, Amaret Chalhoub, Beirut
+961 3 679 922 sales@wilfar.com

SAUDI ARABIA
شركة وليم فرحات للديكور
CR# 1009143680
Tamouh Bldg 3rd floor Office 23, Prince Saoud Bin
Abdullah Bin Alwi Street, Al-Quirawan, Riyadh
+966 54 513 3783 sales@wilfar.com

UNITED ARAB EMIRATES
WILFAR L.L.C - FZ
CR# 104551047400001
Meydan Grandstand, 6th floor, Meydan Road,
Nad Al Sheba, Dubai
+971 56 743 5644 sales@wilfar.com